



Applications:

Provide EMC material solutions for EMI & EMS issue for IT devices

- 1.1 Metal rubber absorber to conduct different microwave resonance frequency within the property of loss energy
- 1.2 Noise suppressor for electric devices(Smart phones, Tablets, PCs and etc)
- 1.3 Receiver sensitivity improvement of PEN input (inductive coupling type)
- 1.4 Enhancement of NFC&WPC(PMA/WPC) function within electric devices




performance curve:



TIR™900B-30 Series Thermal Absorbing Materials			
Classification	Unit	Values	Test Method
Color	NA	Gray	Visual
Specific gravity	g/cm ³	3.2	ASTM D297
Surface resistance (min.)	Ω	>1 x 10 ¹²	ASTM D257
Hardness	Shore A	40-60	ASTM D2240
Thermal conductivity	W/mK	3.0	ASTM D5470
Temperature range	°C	-40 to +150	NA
Storage conditions	-	0-30°C/60%±10R.H	NA
Shelf life	month	12	NA
Flame Rating		UL94-V0	E331100
Standard thickness	mm	0.5mmT~5.0mmT	
Standard size	mm	200mmx400mm	

Product identification → TIF9 00 - B - 30 - A1



Gap Fillers | Phase Change Materials | Thermally Conductive Insulators | Thermally Conductive Greases | Thermally Conductive Adhesive Tapes

Canada: TEL: +001-604-2998559 E-mail: sales@thermazig.com	Taiwan: TEL: +886-2-22771007 E-mail: frances@ziitek.com.tw Http://www.ziitek.com.tw	Dongguan: TEL: +86-769-81017480 E-mail: sales@ziitek.com Http://www.ziitek.com	Kunshan: TEL: +86-512-57816297 E-mail: kelvin@ziitek.com Http://www.ziitek.com	Chengdu: TEL: +86-28-62379168 E-mail: sales@ziitek.com
--	--	--	--	---

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.